

VT-447(B)

UL Approval: E214381 Version: B5 /127 /128 /130

Laminate/Prepreg

General Information

- > Halogen Free & High Tg
- > Black, Light Blocking
- > Low Z-CTE
- > UV Blocking

Application

Reinforcement for FPC, Mobile Phone, Smart Phone, Computer, Communication Equipment, Instrumentation, LED, Electronic Game Machine, VCR, etc

Availability

- > Core Thickness: 0.006" (0.15mm) to 0.040" (1mm), other thickness on request
- > Available in roll or panel form
- > Copper Foil: 1/4oz to 12oz
- > E-Glass styles: 7628, 1506, 2116, other glass fabric on request

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.
308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129
T: +86 512-68091810
Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe
Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK
T: +44 1926-889822
Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA
21 Water Street, Amesbury,
Massachusetts, MA 01913,
United States of America
T: +1 978-5219700
Email: saleseast@ventec-usa.com

www.ventecclaminates.com

VT-447(B)

UL Approval: E214381 Version: B5 /127 /128 /130

Laminate/Prepreg

IPC-4101E /127 /128 /130

Properties		Test Method	Units	Specification	Typical Value
Thermal Properties					
Tg	DSC	IPC-TM-650 2.4.25	°C	–	–
	TMA	IPC-TM-650 2.4.24	°C	170 minimum	180
Td		ASTM D3850	°C	–	380
T260		IPC-TM-650 2.4.24.1	Minute	30 minimum	60
T288		IPC-TM-650 2.4.24.1	Minute	–	–
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	150
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	–	45
	After Tg	IPC-TM-650 2.4.24	ppm/°C	–	190
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	–	2.3
CTE		IPC-TM-650 2.4.24	ppm/°C	–	11~12
MOT		UL 94	°C	–	130
Electrical Properties					
DK (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	–	5.4 maximum	4.35
DF (RC 50%)	@ 1GHz	IPC-TM-650 2.5.5.9	–	0.035 minimum	0.013
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+3 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+4 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+3 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 4 (100-175)
Arc Resistance		ASTM D495	Second	–	240
Mechanical Properties					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	6~8 (1.05~1.40)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	–	6~8 (1.05~1.40)
Flexural Strength	Warp	IPC-TM-650 2.4.4	KPsi (MPa)	60 (415) minimum	72 (500)
	Fill	IPC-TM-650 2.4.4	KPsi (MPa)	50 (345) minimum	58 (400)
Physical Properties					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	0.80 maximum	0.35
Flammability		UL-94	Rating	V0 minimum	V0

Note: All test data provided are typical values and are not intended to be specification values.

CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.

308 TaiShan Rd,
New District Suzhou,
Jiangsu, P.R. China 215129

T: +86 512-68091810

Email: sales@ventec.com.cn

EMEA REGIONAL HEADQUARTERS

Ventec Europe

Unit 1 Trojan Business Centre,
Tachbrook Park Estate,
Leamington-Spa, CV34 6RH, UK

T: +44 1926-889822

Email: sales@ventec-europe.com

AMERICAS REGIONAL HEADQUARTERS

Ventec USA

21 Water Street, Amesbury,
Massachusetts, MA 01913,
United States of America

T: +1 978-5219700

Email: saleseast@ventec-usa.com

www.ventec laminates.com